



safetoe
TOP QUALITY SINCE 1984

Top Quality
Creative Design
Amazing Comfort



Keep Worker in Safe!

M-8387 MP S3 SR

Metatarsal Protection Work Boots

+300° **HOT**
RESISTANT 



Upper : Full Grain Cow Leather + Protective Hard Cover

Thread: Fire-resistant Kelvar Stitching

Lining : Beathable Sandwich Mesh

Insole : Super Memory Foam Insoles

Outsole : PU/Rubber Injection (300°C HRO)

Toecap : Composite Toecap

Penetration : Kevlar Midsole Plate

Size : EU 37-47#, UK 3-13#, USA-14#

CE EN ISO 20345:2022 S3S SR CI HI FO HRO

ASTM E 2149-2020 Approved Anti-microbial Lining & Insoles (Odor Resistant)

Application : Welding, Metal Smelting, Mining, Construction, Mechanics, Oil & Gas Industry etc



200 JOULE
TOECAP



SLIP-
RESISTANT



SHOCK
ABSORPTION



ANTI-STATIC



ANTI-NAIL
MIDSOLE



PETROL AND
CHEMICAL
RESISTANT



WATER
RESISTANT




OIL
RESISTANT



Composite Toe Cap Protection • EN ISO 20345:2022

Compoiste Toecap is light-weight and non-magnetic. The impact resistance can reach 200 joules from falling or rolling objects. The compression resistance can reach 1500kN.



Kevlar Plate Protection (Type PS) • EN ISO 20345:2022

Kevlar midsole plate is flexible and non-metallic. The penetration resistance can reach 1100 newtons from nail or other sharp objects. The flex resistance can reach to 1 X 10⁶ flexion cycles without visable cracking.



Water Resistant Cow Leather Upper • EN ISO 20345:2022

High quality full grain palm printed cow leather with thickness 1.6-1.8mm. It is treated with water resistant coating to protect feet from raining workday. The tear strength of upper leather can reach to 120 Newtons.



Heavy Duty PU/Rubber Outsole • EN ISO 20345:2022

PU/Rubber outsoles are manufacturerd with Germany Fully Automatic Injection Technology. The midsole is 45±5 degree hardness PU, which is soft and shock absorption. The outsole is natural rubber with 5%-10% nitrile, which is abrasion resistant, slip resistant, oil resistant and heat resistant.

Sole Bonding Strength Test

- EN ISO 20345:2022, 5.3 (Between Upper & Sole)
- Average Test Result 5.8 ± 5 (N/mm)



Upper, Lining & Bonding Strength Test Result

Leather Tear Strength \geq	120.0 Newtons
Leather Tensile Properties \geq	15.0 N/mm ²
Lining Tear Strength \geq	15.0 N/mm
Bonding Strength \geq	4.0 N/mm

✓ Protection With Slip Resistant (SR)	Result
Test Requirement : Forward Heel Slip ≥ 0.31 (Test methodL ISO 13287:2019) Backward Forepart Slip ≥ 0.36 (Test methodL ISO 13287:2019)	PASS
Standards : EN ISO20345:2022(5.3.5) , Test floor: Ceramic tile, Lubricant: Sodium lauryl sulphate	
✓ Protection Against Heat Risk & Fire Sparkle 300°C	Result
Test Requirement : The Outsole Did Not Melt & Did Not Develop Any Cracks When Bent Aound Mandrel	PASS
Standards : EN ISO 20345:2022(6.4.1). 300°C HRO=Heat Resistant	
✓ Protection Resistant to Fuel Oil (FO)	Result
Test Requirement : Change in Volume and Change in Hardness (Outsole) is No More Than +12%(*)	PASS
Standards : EN ISO 20345:2022 (6.4.2)	
SAFETOE Standard Package Instruction (Average 42# for Reference)	
Shoes Weight : 1.2-1.3 KGS /Pair	Carton Weight : 13-14 KGS /Carton
1 Pair / Color Box , Dimensions : 32×24×12CM	10 Pair / Carton , Dimensions : 62×49×33CM



User Instructions:

- 1.) RECOMMENDED TO USE : Construction, Logistics, Mechanics, Glasses Installation, Workshop, Farming, Garden, Oil & Gas, Chemical Factory etc.
- 2.) LIMITATION TO USE: It is very important that footwear selected must be suitable for the right workplaces. The protection against risks or hazards which are not mentioned in this document is not warranted.
- 3.) FITTING & SIZE: All footwear are marked with standard size on tongue label. Some are with different size comparison, such as EU size, UK size, US size etc. Please wear footwear in a suitable size.

Footwear which are too loose or too tight may not provide optimum level of protection.

4.) STORAGE: Keep the footwear in its original packaging, under ordinary temperature, non-humidity conditions and in clean, covered and ventilated premises.

5.) CLEANING: Clean footwear regularly by high quality cleaning treatments recommended as suitable for the purpose. Don't use caustic or corrosive cleaning agents.